



RNA-F

Flexi Rose

Pink- orangey pink alloys. For 9-18kt gold alloys.

Unique Characteristics	Flexible 9-18kt use
Purpose	Versatility for manufacturing 9-18K Rose Gold Alloys
Category	Basic
Supply Forms	Pellets
Manufacturability	Casting/Sheet Production/ Wire-Drawing
Patent	
Content, Wt%	Copper, Proprietary Ingredients
ROHS compliance	Yes

Product Code	RNA-F
Product Name	Flexi Rose
PHYSICAL PROPERTIES	
Density, g/cm ³	17.83
Grain Size, μ m	160
OPTICAL PROPERTIES	
Colour	
L*	85.36
a*	5.64
b*	20.32
THERMAL PROPERTIES	
Liquidus, °C	880
MECHANICAL PROPERTIES	
Ultimate tensile strength, Mpa	566
Elongation, %	44
Hardness, as cast, HV	100
Hardness, annealed, HV	80
Hardness, age- hardened, HV	220
Hardness, after reduction (70%	
Electrical Resistivity Ω -m	
PROCESSING & TECHNICAL PROCEDURES	
General Technical Understanding	0
Mixing Temperature, °C	900
Instructions/ Directions for Use	Add this master alloys in pellet form for making 75% gold alloys.. Measure 25wt% (for 18kt) of master alloys and put it at the bottom of the crucible, sprinkle some brazing flux or borax over it. Add the remaining 75 wt% of pure gold on top of the master alloy, heat to 900 °C and hold till it melts, use a graphite and stir the molten alloy to give a homogeneous mixture, then pour out.
Recycling/ Remelting	Up to 5 times investment casting process. Can be better with Vacuum Casting
Casting	
Systems Type	Any
Casting Temperature °C	900-925
Investment/Lost Wax Casting Temperature, °C	900-926
Flask/Cylinders Preparation Temperature °C	500
POST PROCESSING PROPERTIES	
Investment Removal Instructions	soak in hot water
Pickling	Most standard investment removers will successfully remove the investment powder. The best solutions are the sulfuric and hydrofluoric based products. It is better not to use acid solutions, which do not contain sulfur. You can use citric acid at 10%-15% At 60°C changing the solution frequently.
Age Hardening	Age harden for 60 mins or after casting air cool 200 °C
WORKING PROPERTIES	
<i>Sheet Rolling</i>	
Pouring Temperature	900
Maximum Reduction,%	60
<i>Wire-Drawing</i>	
Pouring Temperature	900
Maximum Reduction,%	60
Soldering	As per normal methods
Flux	
Weldability	
Finishing Properties	
Tumbling	As per normal methods
Polishing	
Plating	

Autium Materials Pte. Ltd believes the information presented above to be reliable. However, the information is provided by Autium Materials Pte. Ltd. without charge and users shall employ such information at their own discretion and risk. It is therefore imperative that users test our products and information to determine their suitability prior to intended uses and purposes.

All express or implied warranties, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose, are specifically disclaimed. Any information or recommendation not presented above is unauthorized and shall not bind Autium Materials Pte. Ltd. Autium Materials Pte. Ltd. assumes no legal liability or responsibility for results obtained or damages incurred from the use of such information in whole or in part.